

TECHNICAL DATA SHEET

Heresite P- 413

**Baked Phenolic Epoxy
Protective Coating For
Harsh Environment**

by



Certified Applicator in South East Asia

LINE: @CIGCARE



CIG BLUSOLUTIONS CO., LTD.

Customer Hotline | +66 92.463.2366
+66 2976.5290 | FAX +66 2967.5023
contact@cigblusolutions.com | www.cigblusolutions.com

Head Office Address:
1/1 Moo 7 Bangkoowad Road, Bangkoowad,
Amphoe Muang, Pathumthani 12000 Thailand.

HERESITE®
PROTECTIVE COATINGS, LLC

Heresite P-413

TECHNICAL DATA SHEET



Our 50 years of coating history speaks for itself.

In 1964, Heresite was the first company to apply coatings to aluminum-finned, copper-tubed heat exchangers. The Heresite coating became then, and still remains a standard in the industrial coatings industry. We provide the highest quality protective coatings for air conditioning and refrigeration systems that operate in moderate to severely corrosive environments, including both coastal and/or industrial applications. Our phenolic epoxy has an advantage of dense cross linking and can therefore be applied as a very thin film maintaining stable heat transfer.

We continue our focus on innovation and again have a new story to tell, as we introduce our updated P-413

- A high performance phenolic epoxy coating developed specifically for heat exchangers.
- The flexibility and corrosion resistance of Heresite P-413 appreciably increases the service life of your heat exchange equipment.
- It is specially suited for coating light gauge metals in equipment operating in severe corrosive environments.

P-413 Specifications

The coil will receive a uniform coating on all surfaces, including fin edges, with P-413, a thermoset, modified phenolic coating. Application of P-413 will be through multiple coats by immersion or flow coating to a film thickness of approximately 1.0 mil.

P-413 provides corrosion protection in a 18,000 hour salt spray test in accordance with ASTM B-117 and humidity resistance of >2,000 hours per ASTM D2247. Chemical resistance is demonstrated via 100+ acetone double-rubs per ASTM 5402.

P-413 also exhibits superior hardness of 5-6H per ASTM D3363, adhesion of 5B per ASTM B3359 and impact resistance of 160 in/lbs (ASTM D2794). Color shall be brown with gloss of 20-60 — 60 degree. If the coils are to be subjected to direct ultraviolet (UV) exposure, a spray-applied UV-resistant topcoat is an option.

P-413 Typical Properties (@ 1 mil DFT)

Salt Spray: ASTM B-117: 18,000 hours

SWAAT: ASTM G85-11 Section A.3: Passed 1,000 hours using pressurized coil (see page 2 for results)

Cyclic Weathering: ISO 20340 Offshore Standard: Passed (4,200 hours)

Performance Testing: ISO 12944-6 C5 I/M: Passed C5-M high durability and C5-I high durability

Heat Transfer Reduction: <1% as applied for heat transfer components

Humidity: ASTM D-2247: 2,000+ hours

Simulated Sea Water Resistance: 2,000 hours

Solvent Resistance: ASTM-D5402: 100 acetone double rubs

Cross-hatch Adhesion: ASTM D-3359: 5B

Mandrel: ASTM-D522: >1/4 inch

Impact: ASTM D-2794: 160 lb/inch steel; 40 lb/inch aluminum

pH Range (14 day liquid spot test): 2.4-12.6

Temperature Cycling (4 hours at -75°C; 4 hours at 190°C): 4B-5B adhesion after 5 cycles

Dry Heat Resistance (4 hours at 200°C; 20 minutes at 232°C): 4B-5B adhesion after 5 cycles

Dry Film Thickness: ~1 mils

Hardness: ASTM D3363: 5-6H

Gloss: 20-60 on 60 degree meter (topcoat dependent)

Microchannel Compatible

Abrasion Resistance: 30-40 mg loss per 1,000 cycles

Meets FDA 175.300 for indirect food contact

Meets MIL Spec: MIL-C-18467, MIL-E-480 and MIL-STD-883 Method 1101

Meets Other Specs: Honeywell MC 7200-01 and GE F50T17

Thermal Conductivity: At approximately 2 mils thickness, Thermal Conductivity is less than 1.0 w/mK

Dielectric Strength [ISO2376:2010(e)]: 286 volts per mil of thickness



NSF Certified – ANSI 51 Certification of Coatings for Food Zone – Non Contact

Effective date: 07/31/20

CIG edit date: 08/27/21

page 1 of 6

LINE: @CIGCARE



CIG BLUSOLUTIONS CO., LTD.

Customer Hotline | +66 92.463.2366
+66 2976.5290 | FAX +66 2967.5023
contact@cigblusolutions.com | www.cigblusolutions.com

Head Office Address:
1/1 Moo 7 Bangkoowad Road, Bangkoowad,
Amphoe Muang, Pathumthani 12000 Thailand.

HERESITE
PROTECTIVE COATINGS, LLC

Heresite P-413

TECHNICAL DATA SHEET



Certified Applicator in South East Asia

SWAAT Results

	<p>Bare 1,000 hour SWAAT</p>
	<p>P-413 1,000 hour SWAAT</p>
	<p>P-413 + topcoat 1,000 hour SWAAT</p>

Effective date: 07/31/20

CIG edit date: 08/27/21

page 2 of 6

LINE: @CIGCARE



CIG BLUSOLUTIONS CO., LTD.

Customer Hotline | +66 92.463.2366
+66 2976.5290 | FAX +66 2967.5023
contact@cigblusolutions.com | www.cigblusolutions.com

Head Office Address:
1/1 Moo 7 Bangkoowad Road, Bangkoowad,
Amphoe Muang, Pathumthani 12000 Thailand.

HERESITE®
PROTECTIVE COATINGS, LLC

Heresite P-413

TECHNICAL DATA SHEET



Product Description

Baking cross-linked phenolic epoxy

Recommended Uses

Heresite P-413 is a high performance coating used principally for heat transfer components and parts — especially air conditioning and refrigeration systems that operate in moderate to severely corrosive environments, including both coastal and/or industrial applications. This phenolic epoxy has an advantage of dense cross linking and are therefore highly corrosion resistant even when applied as a very thin film.

Chemical Resistance

P-413 is chemically resistant to a wide range of acids, solvents, and inorganic salts. Please review chemical resistance guide for further information.

Packaging Information

P-413 is available in one gallon, five gallon and 54 gallon drum quantities.

Thinners and Cleanup

Recommended use of Heresite S-275.

Storage Conditions

Coating should not be stored longer than 6 months. Coating should be stored in a clean, dry environment at 50–75°F. Keep out of direct sunlight. Avoid excessive heat and keep from freezing.

Physical Properties

Solids by weight: Approximately 73%

Solids by volume: Approximately 57%

Pot life: NA

Mixing Ratio by Volume: NA 1 component

Shelf life: 6 months

Color: Brown

VOC Content

2.25 lbs/gal (270 g/L) as supplied

Film Thickness

For heat transfer, a 2 coat immersion process will typically yield a dry film thickness of 1.0–2.0 mils (25–50 microns).

For other parts, please contact Heresite.

Coverage

Theoretical coverage is 800 square feet per gallon per dry mil. Coverage rates are estimates and make no allowance for material loss. Actual rates will vary dependent on application method, surfaces, etc.

Surface Preparation

All surfaces must be clean, sound, and free of any oils, dirt, grease, wax and any other contamination that may interfere with coating adhesion.

In general, the surface should be cleaned by solvent or a cleaner at elevated temperature followed by a clean water rinse. Rinse water shall have a conductivity of lower than 500 microsiemens and a neutral pH (7.0–8.0). All surfaces must be dried prior to application of coating.

In cases where there is a large amount of contamination or heat treated steel, a commercial blast is acceptable in accordance with NACE #3 or SSPC-SP-6-63 specifications. Surface profile or anchor pattern shall be 20–25% of the recommended dry film thickness.

Thinning

Reduce P-413 with S-275 solvent to 15 – 17 seconds on ISO Dip 3 mm Mini Cup (13–13.5 seconds for spray).

This requires approximately a 1:1 dilution by volume.

The amount of thinner required is dependent upon temperature, ventilation, humidity, application type and desired film thickness.

Effective date: 07/31/20

CIG edit date: 08/27/21

page 3 of 6

LINE: @CIGCARE



CIG BLUSOLUTIONS CO., LTD.

Customer Hotline | +66 92.463.2366

+66 2976.5290 | FAX +66 2967.5023

contact@cigblusolutions.com | www.cigblusolutions.com

Head Office Address:

1/1 Moo 7 Bangkoowad Road, Bangkoowad,
Amphoe Muang, Pathumthani 12000 Thailand.

HERESITE
PROTECTIVE COATINGS, LLC

Heresite Certified Applicator

This certifies that



C.I. Group Public Company Limited is certified to apply
Heresite Baked Phenolic Epoxy P-413

Certified on this date
01 July 2021

Peter Hellman

Peter Hellman, Owner

